



## AURIGIN® SUMMARY PAGE

(11) Publication number: 02732999 B2

(45) Publication Date: 30 . 03 . 98

Application Publication No.: 06207382 A2

(43) Date of publication of application: 26 . 07 . 94

(51) Int. Cl. 6D06P 5/00 6B41J 2/01 6B41M 5/00 6D06P 5/12

(21) Application number: 05017902

(22) Date of filing: 07 . 01 . 93

(30) Priority: 07 . 01 . 93 JP 17902

(71) Applicant: KANEBO LTD

(72) Inventor:  
 KUSAKI KAZUO  
 NUNOO TOSHIICHI  
 MORIMOTO KAZUYOSHI  
 IWATA KAZUO  
 NISHIMURA MICHIO

(54) METHOD FOR PREVENTING DEVICE BY INK  
JET METHOD

## (57) Abstract:

PURPOSE: To simply obtain a high grade resist-printed product without causing the bleeding of dyestuffs by printing an ink containing a nondischargeable dyestuff on a web by a jet printing method, applying a reducing agent to the printed pattern and subsequently dyeing the dyed web with a dischargeable dyestuff.

CONSTITUTION: Woven fabric or nonwoven fabric comprising natural fibers, semisynthetic fibers, synthetic fibers is printed with an ink containing a dyestuff not decomposed with a reducing agent by an ink jet method for forming a printed pattern, and

subsequently dried. A dyeing-preventing sizing agent containing the reducing agent is screen-printed on the formed pattern, and dried. The printed fabric is printed with a printing dyestuff color sizing agent containing a dyestuff capable of being decolorized with the reducing agent, dried and subsequently thermally treated with steam to easily provide a high grade colored, resist-printed pattern brilliant in pattern edges and free from the bleeding of the dyestuffs by the ink jet method. A direct dyestuff, reactive dyestuff, acidic dyestuff, cationic dyestuff, disperse dyestuff, or naphthol dyestuff can be used as the dyestuff according to the kinds of the fibers. The fabric is preferably preliminarily subjected to a water-repelling treatment.

COPYRIGHT: (C)1994,JPO&amp;Japio